



PAIRUI

FUAN

Ferrite Cores T48*30*15


P3 - T48*30*15 - C/P

P3 : Material .
 T48*30*15 : Core Size.
 C/P : Coating.
 C=Epoxy;P=Parylene.



Dimension: (UNIT:mm)

	Dimensions (mm)	Epoxy Coating Dimensions(mm)
OD	48.00 ± 0.50	49.40max
ID	30.00 ± 0.50	28.60min
HT	15.00 ± 0.40	16.00max



Effective parameter

Le(mm)	Ae(mm ²)	Ve(mm ³)	Wt(g/set)
122.52	135.00	16540.49	≈ 79.39


Test conditions

AL: F=10.0KHz U=0.1V N=10Ts (HP-4284A) .
 Coating The core are coated with epoxy, flame retardant in accordance with "UL 94V-0"file number E228348. The colour is green.


Ring core data

AL(nH)	μi	Type Number
3185 ± 25%	2300	T48*30*15 - P3
6923 ± 30%	5000	T48*30*15 - H5K
9692 ± 30%	7000	T48*30*15 - H7K
13846 ± 30%	10000	T48*30*15 - H10K


Complex permeability versus frequency (measured with T10 ring cores, B≤0.25mT)




Complex permeability versus frequency (measured with T10 ring cores, B≤0.25mT)



Complex permeability versus frequency (measured with T10 ring cores, B≤0.25mT)



Complex permeability versus frequency (measured with T10 ring cores, B≤0.25mT)



Note:

- 1:Document is the property of FUAN Inc & is not allowed to be duplicated without authorization
- 2:ROHS compliant.